

Material	Tip	Rm(Mpa)		Rp0,2(Mpa)	Alungire (%)	Duritate HV		Conductibilitate electrica	
		min.	max.		A50 mm	min.	max.	MS/m min.	% IACS min.
Cu-DHP	R 220 moale	220	260	max. 140	min. 33	40	65		70 - 90
Cu-DHP	R 220 semi-dur	240	300	min. 180	8	65	95		
SF-Cu	F 24 semi-dur	240	300	min. 180	8	65	90		
OF-OK	R 220 moale	220	260	max. 140	min. 33	40	65	58	100 - 102
Cu-ETP	R 240 semi-dur	240	300	min. 180	8	65	95	57	98,3